

Variety	Staple Length	Micronaire	Strength	Uses In	Comparable Foreign Growths
MCU-5	32 to 34mm	3.2 to 3.7	30 GPT (HVI)	Spinning	U.S. Ultima RG, Egyptia Giza86/Giza89, Sudanese Barakat
Shankar – 6	27.5 to 29.5mm	3.5 to 4.9	28 GPT (HVI)	Spinning	U.S. Fibre Max/Acala, W.African, Australian, Brazilian, Tanzanian, Syrian
MECH-1	27 to 29mm	3.5 to 4.9	27 GPT (HVI)	Spinning	W.African, Brazilian, Tanzanian, Paraguayan, Argentine
J34	24 to 27mm	4.0 to 4.9	26 GPT (HVI)	Spinning	U.S. MOT, Pakistan Afzal 1467
Bengal Desi	12 to 14mm	5.0 to 7.0	18 GPT (HVI)	Medical	
V797	20 to 22mm	4.5 to 6.0	24 GPT (HVI)	Spinning	
Y1	23 to 25 mm	4.0 to 5.5	15 GPT (HVI)	Spinning	U.S. MOT, Pakistan Afzal